

COVALENCE® PERP

Product Information

Repair system for damaged mill-applied PE coating.

Product description: Covalence® PERP is a heat-applied patch which, in combination with mastic filler, offers an economically effective and high quality repair system for factory PE pipe coatings damaged mechanically during transportation, storage and laying of pipes. PERP, PERP80 and PERP60E are designed to repair the damaged areas on line coatings, mainly 2 or 3 layer PE. PERP60E is designed to repair the damaged areas on PE coated pipes used in high shear applications, such as directional drilling.

- Sleeves: are recommended for large damaged areas (see selection table below).
- Filler tape: is used to fill the holiday, thus restoring the mill-applied coating thickness of the pipe.
- Epoxy primer: is additionally used when reinstatement of the epoxy layer is required.

Construction: Two-layer or three-layer system:

- First layer. Liquid epoxy, solvent-free two-component (optional).
- · Second layer. Copolymer adhesive
- · Third layer. Radiation cross-linked, high density polyethylene (unexpanded).

Installation is done with standard gas torches. To repair a damaged area, installers round out, roughen, clean and preheat the area and apply the filler tape to fill out the holiday. PERP, cut to size, is positioned onto the treated area and heated. During heating, the adhesive softens and flows to form a tight bond with the substrate. The bond strength builds up during cool-down and is fully retained after job completion.

- · Adaptable repair system.
- Resistant to high shear forces.
- Excellent adhesion to commercial, PE mill-applied coatings.
- · No special equipment required.

Benefits:

- Long lasting and high performance.
- Provides a virtually monolithic coating repair of high quality.
- Saves time with fast and convenient installation. Saves money by keeping inventory and logistics costs low.
- Makes installation fast and easy. Keeps installation costs low.

Product selection guide				
	PERP	PERP80	PERP60E	
Max operating	65°C	80°C	60°C	
temperature	(149°F)*	(176°F)	(140°F)	
Compatible line	PE, FBE,	PE, FBE,	PE, FBE	
coatings	PP, PU	CTE		
Min. preheat temperature				
Bare metal	70-80°C	70-80°C	70-80°C	
	(158-176°F)	(158-176°F)	(158-176°F)	
Line coating	70-80°C	90-100°C	70-80°C	
	(158-176°F)	(194-212°F)	(158-176°F)	
Recommended pipe	ST3 or	ST3 or	SA21/2	
preparation	SA2½	SA2½		
Filler tape	S1137-	S1137-	S1182-	
	50X3X3000	50X3X3000	50X3X3000	
Epoxy primer	S1239 or	S1301-M or	S1239 or	
(optional)	S1301-M	S1401(-M)	S1301-M	
Soil stress restrictions	None	None	None	
Performance	EN12068,	EN12068,	EN12068,	
	Class C50	Class C80	Class C60	
* Man 7000 (45005)laara			0.0.00	

^{*} Max.70°C (158°F) when used a repair to HSS under infill.

Product propertie	es .			
Backing				
Property	Test method	l Typica	nl value PER 8 PERP6	RP, PERP80 GOE
Tensile strength at	ASTM D-638		3300 ps	
break			22.8 MP	а
Elongation at break	ASTM D-638		600%	
Hardness, Shore D	ASTM D-2240)	55	
Shrink force	ASTM D-638		40 psi	
	@ 150°C			
Dialografia atnovemb	(302°F) ASTM D-149		900 V/m	:1
Dielectric strength	ASTM D-149		35 kV/mi	
Moisture	ASTM D-570		0.05%	111
absorption	7.01111 2 070		0.0070	
Adhesive				
Property	Test method		Typical va	alue
		PERP	PERP80	PERP60E
Softening point	ASTM E-28	103°C	120°C	94°C
		(217°F)	(248°F)	(201°F)
Shear strength	ASTM D-	350 psi	750 psi	500 psi @
	1002	@ 23°C	@ 23°C	23°C
	_	(73°F) 11 psi @	(73°F) 65 psi	(73°F) 87 psi
		65°C	@ 80°C	@ 50°C
		(149°F)	(176°F)	(122°F)
-	EN12068	0.22	0.12	0.32
		N/mm ²	N/mm ²	N/mm ²
		@ 50°C	@ 80°C	@ 60°C
In stallant alance		(122°F)	(176°F)	(140°F)
Installed sleeve	Tool		Tuningles	luc
Property	Test method		Typical va	iue
	method	PERP	PERP80	PERP60E
Peel to PE	ASTM D-	25 lb/in	21 lb/in	60 lb/in
. 551 10 1 2	1000	_5 10/111	_ 1 10/111	00 10/111
	EN12068	3.5	3.5	20
		N/mm	N/mm	N/mm
Impact resistance	EN12068, Class C	>15 J	>15 J	>15 J
Indentation	EN12068,	Pass	Pass	Pass
	Class C	@ 50°C	@ 80°C	@ 60°C
		(122°F)	(176°F)	(140°F)

Note: The typical values in this data sheet are based on lab prepared samples. Values shown are not to be interpreted as product specifications.

Product thickness		
	_ PERP - PERP80	PERP60E
Backing as supplied	0.76 mm	0.76 mm
	(0.030 in)	(0.030 in)
Adhesive as supplied	0.65 mm	0.80 mm
	(0.026 in)	(0.031 in)

Order information		General order information		
Covalence® PERP type prod	ducts are available	Installation guide	For proper product installation, see latest installation instruction.	
As a kit		Handling	Handle with care. Keep boxes upright.	
- As a roll		Storage	Store indoor, clean and dry, away from direct sunlight in a cool place below +50°C. Unlimited	
Example:			shelf life.	
	Standard ordering options	Information		
PERP-KIT	1 pc PERP patch 170 mm x140 mm with rounded corners, 1 pc S1137 (50x3x25 mm), 1 pc abrasive paper P60 (150x50 mm), installation instruction For damaged areas less than 40x70 mm	Documentation	Extensive information is available on our web- site. Application instructions and other documentation can be obtained by contacting our head office, from our local distributor or by sending an email to info@sealforlife.com	
PERP-170X10,000	Roll of 10 m (32.5 ft) length, 170 mm (6.75") width	Certified staff	Application of the described coating system shall be carried out by certified personnel.	
PERP-425X10,000	Roll of 10 m (32.5 ft) length, 438 mm (17.25") width			
PERP80-425X1000-PCI	PCI = Permanent Change Indicator			
PERP60E-425X10,000PCI	(embossed backing)			
S1137-50x3x3000	50 mm (2") wide, 3 mm (0.12") thick, 3 m (10 ft) long Filler adhesive for PERP + PERP80			
	Filler adhesive, necessary where PERP rolls are used. NOTE: 3 rolls of filler per roll of PERP are recommended.			
S1182-50X1X9000	50 mm (2") wide, 1 mm (0.039") thick, 9 m (30 ft) long Filler adhesive for PERP60E			
	Fillier adhesive, necessary where PERP60E rolls are used. NOTE: 3 rolls of filler per roll of PERP are recommended.			
PERP-280X280-05	Kit of 2 pcs PERP-280x140-05 with punched hole			
	To be used with HTTE, house tap tee protection			
S1239 or S1301-M S1301-M or S1401(-M)	Epoxy primer For PERP + "PERP60e For PERP80			
. ,	Only when 3-layer coating			

Application table		
Max.damaged area for using PERP. *		
Pipe diameter	Max.damage	
<10"	50 mm x 50 mm	
<30"	100 mm x 100 mm	
>= 30"	150 mm x 150 mm	

^{*} For larger damaged areas, the use of heat-shrinkable sleeves is recommended (refer to Covalence girth weld sleeves).





Seal For Life Industries LLC Franklin, MA, USA
Tel: +1 508 918 1600
Toll Free: +1 800 248 7659
Fax:+1 508 918 1905
franklin@sealforlife.com

Seal For Life Industries Mexico S de R.L. de C.V.
Tijuana, Mexico
Tel USA: +1 858 633 9797
Fax USA: +1 858 633 9740
Tel Mx: +52 664 647 4397
Fax Mx: +52 664 607 9105
mexico@sealforlife.com

Seal For Life Industries Stopaq B.V.
Stadskanaal, the Netherlands
Tel: +31 599 696 170
Fax: +31 599 696 177
info@sealforlife.com Seal For Life Industries BVBA Westerlo, Belgium Tel: +32 14 722 500 Fax: +32 14 722 570

Seal For Life India Private Ltd. Baroda, India Tel: +91 2667 264 721 Fax: +91 2667 264 724

Anodeflex® - Stopaq® - Polyken® - Covalence® - Powercrete® - Sealtaq® - Blockr® - Easy.Qote®

DISCLAIMER: Seal For Life Industries warrants that the product(s) represented within conform(s) to its/their chemical and physical description and is appropriate for the use as stated on the respective technical data sheet when used in compliance with Seal For Life Industries written instructions. Since many installation factors are beyond the control of Seal For Life Industries, the user is obligated to determine the suitability of the products for the intended use and assume all risks and liabilities in connection herewith. Seal For Life Industries makes no other warranty either expressed or implied. All information contained to the respective technical data sheet(s) should be used as a guide and is subject to change without notice. This document supersedes all previous revisions. Please see revision date on the left. Covalence® is a registered trademark of Seal For Life Industries.