

COVALENCE® PE MELT STICK

Product Information

Repair system for damaged mill-applied PE coating.

Product description: PE MELT-STICK is a heat-sensitive, PE copolymer-based stick used for small superficial, damage (scratches) to PE-coatings where the damage does not extend to the bare metal. Maximum damaged area can be 25 mm by 25 mm or 6.25 cm².

Installation is done with a standard gas torch. After eliminating all sharp edges, cleaning and preheating, PE-MELT-STICK is heated above the damaged area until becoming glossy. No filler is required. The molten adhesive is spread onto the scratches, forming a tight bond with the substrate. After cool down, the hardening adhesive is smoothed flush with the PE line coating using a paint scraper.

Features:

- Versatile and adaptable repair system.
- Resistant to high shear forces.
- Excellent adhesion to commercial PE mill-applied coatings.
- Simple stick form.
- No special equipment required.

Benefits:

- Highly economical.
- Double reconstruction of the damaged coating.
- Guarantees a virtually monolithic coating repair of high quality.
- Makes installation faster and more convenient – saves time.
- Makes installation fast and easy. Keeps installation costs low.

Product selection guide

Max operating temperature	85°C (185°F).
Compatible line coatings	PE
Min. preheat temperature	60-70°C (140-158°F)
Recommended pipe preparation	Brush
Soil stress restrictions	None

Product dimensions

Length	305 mm (12 in)
Diameter (mm)	25 mm (1 in)

Product properties

Adhesive

Property	Test method	Typical value
Softening point	ASTM E28	120°C (248°F)
Shear strength	ASTM D1002	750 psi
	@ 23°C (73°F)	65 psi
	@ 80°C (176°F)	

Installed sleeve

Property	Test method	Typical value
Peel to PE	ASTM D1000	16 lb/in

Product order information

Covalence® PE-MELT-STICK type products are available

– As a stick

Example PERP-MELT-STICK(S50)

Standard ordering options

PERP-MELT-STICK (S50)	Ø 25 mm x 305 mm
	Packed per 50 pc in a bag

General Information

Installation guide	For proper product installation, see latest installation instruction.
Handling	Handle with care. Keep boxes upright.
Storage	Store indoor, clean and dry, away from direct sunlight in a cool place below +50°C. Unlimited shelf life.
Documentation	Extensive information is available on our web-site. Application instructions and other documentation can be obtained by contacting our head office, from our local distributor or by sending an email to info@sealforlife.com
Certified staff	Application of the described coating system should be carried out by certified personnel.

DISTRIBUTOR LOCAL/REPRESENTANTE:



SEALFORLIFE Industries
 PART OF THE BERRY PLASTICS ENGINEERED MATERIALS DIVISION

Seal For Life Industries LLC
 Franklin, MA, USA
 Tel: +1 508 918 1600
 Toll Free: +1 800 248 7659
 Fax: +1 508 918 1905
franklin@sealforlife.com

Seal For Life Industries Mexico
 S de R.L. de C.V.
 Tijuana, Mexico
 Tel USA: +1 858 633 9797
 Fax USA: +1 858 633 9740
 Tel Mx: +52 664 647 4397
 Fax Mx: +52 664 607 9105
mexico@sealforlife.com

Seal For Life Industries
 Stopaq B.V.
 Stadskanaal, the Netherlands
 Tel: +31 599 696 170
 Fax: +31 599 696 177
info@sealforlife.com

Seal For Life Industries BVBA
 Westerlo, Belgium
 Tel: +32 14 722 500
 Fax: +32 14 722 570
belgium@sealforlife.com

Seal For Life India Private Ltd.
 Baroda, India
 Tel: +91 2667 264 721
 Fax: +91 2667 264 724
india@sealforlife.com

Anodefex® - Stopaq® - Polyken® - Covalence® - Powercrete® - Sealtaq® - Blockr® - Easy.Qote®

DISCLAIMER: Seal For Life Industries warrants that the product(s) represented within conform(s) to its/their chemical and physical description and is appropriate for the use as stated on the respective technical data sheet when used in compliance with Seal For Life Industries written instructions. Since many installation factors are beyond the control of Seal For Life Industries, the user is obligated to determine the suitability of the products for the intended use and assume all risks and liabilities in connection herewith. Seal For Life Industries liability is stated in the standard terms and conditions of sale. Seal For Life Industries makes no other warranty either expressed or implied. All information contained in the respective technical data sheet(s) should be used as a guide and is subject to change without notice. This document supersedes all previous revisions. Please see revision date on the left. Covalence® is a registered trademark of Seal For Life Industries.